

EN

Preliminary Technical Data Sheet

Bectron®
CG 5660

Printed Electronics - 1 K - Thermal Cure
Electrically Conductive Adhesive (ECA)

ELANTAS Europe Sales offices:

Collecchio (PR) 43044 - Italy
Strada Antolini n° 1 loc. Lemignano
Tel +39 0521 304777 Fax +39 0521 804410

Hamburg 20539 - Germany
Großmannstrasse. 105
Tel +49 40 78946 0 Fax +49 40 78946 349

Quattordio (AL) 15028 - Italy
Via San Martino, 6
Tel +39 0131 773870 Fax +39 0131 773875

AdvancedPrinting@altana.com
www.elantas.com/europe



Description

Bectron® CG 5660 is a single component, conductive, thermal curing epoxide adhesive for electronic application and printing. Bectron® CG 5660 can be used as an Electrically Conductive Adhesive (ECA). In combination with the Non Electrically Conductive Adhesives (NCA) Elan-glue® EP 5360 it is possible to apply wet in wet and cure together.

Key Properties:

- Single component, no mixing required
- 100%-material, solvent free
- Electrical conductivity
- High thermal conductivity
- Temperature curing at 90°C possible
- Dispensable
- Printable
- Very good adhesion on various substrates

Areas of application

Bectron® CG 5660 is designed to be used in printed electronics as an Electrically Conductive Adhesive (ECA) providing a conductive connection between printed silver inks and electronic components. It is also suitable to provide conductive connections on printed circuit boards (PCB). Due to its high silver content Bectron® CG 5660 provides an good thermal conductivity which makes the material suitable as a powerful thermocoupling interface material between non-conductive hot components and metal heat-sinks.

Compatibility with the following conductive screen printing inks has been successfully evaluated:

- Bectron® CP 6662
- Bectron® CP 6668
- Bectron® CP 6681
- Bectron® CP 6680
- Bectron® CP 6690

The material shows excellent adhesion on various substrates.

Material	Adhesion
Steel	+++
Aluminium	+++
Fiber reinforce PC	+++
PET film	+++
Polycarbonate	+++
ELAN-Film® 180	+++

Processing methods

Application: Bectron® CG 5660 can be applied by manual and automated dispensing or in thin layer by screen printing. Dispensing in dots and lines is possible as well for applications on printed circuit boards.

Screen printing equipment: Semi-automatic, manual flatbed

Screen types: 70-100 1/cm stainless steel or polyester

Tension: 25 N/cm, EOM ~ 10-15µm

Squeegee: 75° Shore A, polyurethane at 70° angle, printing speed 50 mm/s

Re-work: Being an adhesive and glue Bectron® CG 5660 can only be removed by mechanical force.

Curing/Post-curing

Bectron® CG 5660 cures by temperature between 80 – 130°C. The higher the temperature, the shorter the cure time. Intrinsic overheating of the resin has to be avoided to obtain full material properties. The evolution of heat is a function of the volume of material used, of the cure temperature, and the capacity of the surrounding to absorb heat - namely the substrates. Both a batch oven as well as conveyer furnaces can be used for thermal cure.

To ensure satisfactory adhesion all surfaces should be dry, clean, and free of residues. Additional activation of the surface may increase the adhesion of the product.

Compatibility of adhesive and respective surface should be checked individually by application.

Successful cure has been obtained e.g. at approx. 45 min at 90°C in bulk or at approx. 10 min at 130°C in thin layer on fiber reinforced polycarbonate (PC), thermally insulating.

Storage and stability

Product should be stored in its original sealed container to avoid any potential contamination at a temperature between -18°C till 8°C. Store accordingly to any specific instruction listed on the product label. Product should be used prior to the expiring date marked on the label. Keeping the material at 25°C for 48h is possible. Keeping the material at higher temperatures and/or longer duration at 25°C the curing reaction will start.

Handling precautions

Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

Typical product characteristics

Properties	Conditions	Test Method	Value	M/U
Colour		--	Silver-grey	
Shelf life	-18°C to 8 °C	Internal Test	6	months
Density	20 °C	DIN 53217	4,6 ÷ 4,8	g/cm ³
Coverage	10 µm layer thickness	Calculated (VdL-RL 08)	19	m ² /kg

Typical mechanical properties of the cured product

Properties	Conditions	Test Method	Value	M/U
Cross-cut test		DIN EN ISO 2409 (Internal Test L42a)	ISO-0	

Typical thermal properties of the cured product

Properties	Conditions	Test Method	Value	M/U
Glass transition temperature (Tg)		TMA (Internal Test M56)	125 ÷ 135	°C
Linear expansions coefficient	above Tg (135 to 190 °C)	TMA (Internal Test M56)	85	ppm/K
	below Tg (-30 to 125 °C)		45	ppm/K

Typical electrical conductivity of the cured product

Properties	Conditions	Test Method	Value	M/U
Sheet resistivity		DIN EN 62899-2 (Internal Test U22)	400	mΩ/sq/mil

Product of ELANTAS Europe. Our advice given verbally or in writing is based on the present state of our technical knowledge, but is intended as information given without obligation, also with respect to any protective rights held by third parties. It does not relieve your own responsibility to check the products for their suitability to the purposes and processes intended and in accordance with the technical sheets of the products. The application usage and processing of the product are beyond our control and will completely fall into the scope of responsibility of buyers and users. Should there nevertheless be a case of liability from our side, this will be limited to any damage equivalent to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our general terms and condition. Product conformity is guaranteed by properties defined in sales specification. Typical properties do not constitute part of the agreed product property or sales specification. Deviation from typical properties does not constitute non-conformity of the product. Typical properties are provided for general information purpose and as a guideline for the choice of the product; they are subject to variation related to i.e. curing cycles, specimen preparation, batch to batch variability, etc. unless specifically agreed with customers.