

EN

Technical Data Sheet

**Bectron®****PT 4600**

Electronic Protection System - UL 94 V-0 listed

Modified Polyurethane - One Component - UV + Moisture Cure  
Thick Film Conformal Coating - Elastic

**ELANTAS Europe Sales offices:**

Collecchio (PR) 43044 - Italy  
Strada Antolini n° 1 loc. Lemignano  
Tel +39 0521 304777 Fax +39 0521 804410

Hamburg 20539 - Germany  
Großmannstrasse. 105  
Tel +49 40 78946 0 Fax +49 40 78946 349

Quattordio (AL) 15028 - Italy  
Via San Martino, 6  
Tel +39 0131 773870 Fax +39 0131 773875

[bectron.elantas.europe@altana.com](mailto:bectron.elantas.europe@altana.com)  
[www.elantas.com/europe](http://www.elantas.com/europe)



## Description

Bectron® PT 4600 is a solvent free one-component polyurethane based transparent thick film coating cured by UV irradiation and / or by moisture.

The cured product is elastic with flexibility down to low temperature (-40°C) and good adhesion to most substrates.

Bectron® PT 4600 provides excellent insulation properties after severe wet storage conditions.

- Satisfies the requirements of ROHS.

## Areas of application

Bectron® PT 4600 is versatile VOC-free conformal coating with excellent electrical performance, particularly suitable for electronics such as surface mount devices and hybrids. It provides good protection against moisture, corrosion and migration as well as vibration.

## Properties of cured product

Bectron® PT 4600 has following properties in cured conditions:

- Thermal cycling over -40°C to +125°C
- Temperature resistance -40 to +125°C
- MIL-I-46058C listed
- Good flexibility to -40°C
- Good Adhesion
- Good dielectric properties
- Solvent free
- UL V0 File No. E211569

## Storage and stability

In closed original containers shelf life of 6 months. Containers should be sealed as the product is moisture sensitive. Storage temperature is depending on the used packaging:

- cartridges: 5 °C to 10 °C  
please note different viscosity: 500-1500 mPas
- 5kg bladder bag: 5 °C to 10 °C  
please note different viscosity: 500-1500 mPas
- 5kg steel pail: 5 °C to 25 °C

## Preparation

The components to be coated should be clean dry and free from grease and compatibility between the resin and all materials on a PCB should be checked prior to use. Residual water from washing the PCB can cause bubbles so low solids flux or alcohol based cleaning materials are recommended.

## Processing methods

Bectron® PT 4600 can be applied by spray, dispensing, jetting and brushing. Complete dipping or selective flooding/dipping can be used in a machine with controlled atmosphere to exclude moisture. Thinner Bectron 300 can be used to remove liquid Bectron PT 4600 and clean the equipment.

## Curing/Post-curing

Curing in UV light requires 5 - 10 seconds, depending of the used type and power of the UV-lamp. A colour change from blue to green/yellow indicates the degree of UV-curing.

Post-curing by moisture in shadow areas takes 2 to 3 days. Full polymerisation of the last <5 % will take place over 2 weeks achieving full properties of the material.

For a usual film thickness of  $200 \pm 50\mu\text{m}$  and  $3000 \text{ mJ/cm}^2$ , curing takes approx. 5 seconds. The conveyor speed should be 1-2.5 m/min to limit influence of heat.

### Caution!

The UV reactivity is high, so sunlight or UV inspection lamps will start pre-curing, preventing the full development of the properties of the coating.

## Handling precautions

Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

## Sales specifications

| Properties | Conditions                                 | Test Method                       | Value     | M/U    |
|------------|--------------------------------------------|-----------------------------------|-----------|--------|
| Viscosity  | 23 °C - Z3, 150 s-1                        | DIN 53019 (Internal Test V18/b/c) | 400 ÷ 900 | mPa·s  |
| Shelf life | 5 °C to 10 °C - cartridges and bladder bag | Internal Test                     | 6         | months |
|            | 5 °C to 25 °C - steel pail                 |                                   | 6         | months |

## Typical system properties

| Properties        | Conditions                 | Test Method                    | Value        | M/U   |
|-------------------|----------------------------|--------------------------------|--------------|-------|
| Temperature range |                            | Internal Test                  | - 40 ÷ + 125 | °C    |
| Density           | 23 °C                      | ISO 2811-2 (Internal Test S11) | 1,06 ÷ 1,16  | g/cm³ |
| UV-curing         | 2500 - 3500 mJ / cm² (UVA) | Intern                         | 3 ÷ 7        | s     |

## Typical mechanical properties of the cured product

| Properties         | Conditions     | Test Method                    | Value   | M/U     |
|--------------------|----------------|--------------------------------|---------|---------|
| Mandrel Bend Test  | 3 mm - 0,06 mm | IEC 60464-2 (Internal Test M4) | 180     | °       |
| Hardness Shore A/1 | 23 °C          | ISO 868 (Internal Test M30b)   | 60 ÷ 70 | Shore A |

## Typical thermal properties of the cured product

| Properties                        | Conditions                     | Test Method             | Value     | M/U   |
|-----------------------------------|--------------------------------|-------------------------|-----------|-------|
| Glass transition temperature (Tg) |                                | IEC 61006               | -15 ÷ -20 | °C    |
| Linear expansions coefficient     | above Tg                       | TMA (Internal Test M56) | 180 ÷ 220 | ppm/K |
| Flammability UL 94 classification | Min Thk 10 mic, Max Thk 55 mic | File No. E211569        | V - 0     |       |

## Typical dielectric properties of the cured product

| Properties                                    | Conditions                      | Test Method                     | Value              | M/U   |
|-----------------------------------------------|---------------------------------|---------------------------------|--------------------|-------|
| Volume resistivity                            | 23 °C                           | IEC 60464 -2 (Internal Test M5) | > 10 <sup>14</sup> | Ω·cm  |
| Dielectric Strength                           | 23 °C                           | IEC 60464-2 (Internal Test M6)  | 70 ÷ 80            | kV/mm |
|                                               | 23 °C - 24 h in deionized Water |                                 | 60 ÷ 70            | kV/mm |
| Volume resistivity after 7 days water storage | 23 °C                           | IEC 60464-2                     | > 10 <sup>13</sup> | Ω·cm  |
| Surface Isolation Resistance (SIR)            |                                 | according IPC TM 650 2.6.3.7    | > 10 <sup>11</sup> | Ω     |

**Product of ELANTAS Europe.** Our advice given verbally or in writing is based on the present state of our technical knowledge, but is intended as information given without obligation, also with respect to any protective rights held by third parties. It does not relieve your own responsibility to check the products for their suitability to the purposes and processes intended and in accordance with the technical sheets of the products. The application usage and processing of the product are beyond our control and will completely fall into the scope of responsibility of buyers and users. Should there nevertheless be a case of liability from our side, this will be limited to any damage equivalent to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our general terms and condition. Product conformity is guaranteed by properties defined in sales specification. Typical properties do not constitute part of the agreed product property or sales specification. Deviation from typical properties does not constitute non-conformity of the product. Typical properties are provided for general information purpose and as a guideline for the choice of the product; they are subject to variation related to i.e. curing cycles, specimen preparation, batch to batch variability, etc. unless specifically agreed with customers.