

EN

Technical Data Sheet

Bectron[®]
SA 70L1-30

Electronic Silicone Adhesive - 1 Part - Neutral cure
High performance Silicon Adhesive

ELANTAS Europe Sales offices:

Collecchio (PR) 43044 - Italy
Strada Antolini n° 1 loc. Lemignano
Tel +39 0521 304777 Fax +39 0521 804410

Hamburg 20539 - Germany
Großmannstrasse. 105
Tel +49 40 78946 0 Fax +49 40 78946 349

Quattordio (AL) 15028 - Italy
Via San Martino, 6
Tel +39 0131 773870 Fax +39 0131 773875

info.elantas.europe@altana.com
www.elantas.com/europe



Description

The Bectron[®] SA 70L1-30 is a 1-part condensation cure products (Alkoxy), non-corrosive when in contact with sensitive electronic parts and substrates. It also provides very good dielectric properties and has excellent adhesion to most common substrates used in the electronic industry. It is an ideal option for many electronic and lighting applications where high performance is a must.

Key properties:

- Neutral cure
- Good dielectric properties
- Self levelling
- Good adhesion to many substrates
- Temperature resistance from -55°C up to 200°C

Areas of application

Assembly and Insulation of electronical and electrical parts and equipment, sealing and bonding of corrosion sensitive devices.

Processing methods

Pre-treatment: Parts to be sealed should be clean dry and free from grease. This product can be applied manually or using automatic dosing systems.

Curing/Post-curing

Following exposure to atmospheric moisture the product will start to cure to a durable silicone elastomer. Skin formation is depending of temperature and should be <80% humidity . At room temperature and 50% humidity the Skin formation will need about 15min. At 25°C and 55% relative humidity a 3 mm section will normally cure in less than 24 hours. Full bond strength and physical properties will be achieved after 5 days. Cure time depends on the thickness of the adhesive applied and shape of the surface exposed to the atmosphere. It is recommended that a minimum thickness of 1 mm is achieved between parts to obtain best adhesion to substrates.

Storage and stability

Products should be stored in their original sealed containers to avoid any potential contamination at a temperature between 5°C and 35°C. Store accordingly to any specific instruction listed on the product label. Products should be used prior to the expiring date marked on the label.

Handling precautions

Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

System specification

Properties	Conditions	Test Method	Value	M/U
Appearance		Visual method	Translucent medium viscosity liquid free from visible impurities	
Density	23 °C	ISO 2811-1 (Internal Test S12)	1,03 ÷ 1,13	g/cm ³

Typical product characteristics

Properties	Conditions	Test Method	Value	M/U
Colour		--	Translucent	
Shelf life		--	12	months
Cure Time	3 mm - 23 °C - 55 %	--	< 24	hrs
Viscosity	23 °C	DIN 53019 (Internal Test V18/b/c)	44000	mPa·s

Typical mechanical properties of the cured product

Properties	Conditions	Test Method	Value	M/U
Tack Free Time	23 °C - 55 %	Internal Test H22	2 ÷ 10	min
Tensile Strength	23 °C	ISO 37 (Internal Test 29)	0,8 ÷ 1,0	N/mm ²
Hardness Shore A/1	23 °C	ISO 868 (Internal Test M30b)	30	Shore A

Typical thermal properties of the cured product

Properties	Conditions	Test Method	Value	M/U
Thermal Conductivity		--	0,2	W/(m·K)

Typical dielectric properties of the cured product

Properties	Conditions	Test Method	Value	M/U
Volume resistivity	23 °C - After 7d water immersion	IEC 60464 -2 (Internal Test M5)	2×10^{14}	$\Omega \cdot \text{cm}$
Comparative tracking index (CTI)	6 mm, test solution C	IEC 60112 (Internal Test M26)	>600	V

Product of ELANTAS Europe. Our advice given verbally or in writing is based on the present state of our technical knowledge, but is intended as information given without obligation, also with respect to any protective rights held by third parties. It does not relieve your own responsibility to check the products for their suitability to the purposes and processes intended and in accordance with the technical sheets of the products. The application usage and processing of the product are beyond our control and will completely fall into the scope of responsibility of buyers and users. Should there nevertheless be a case of liability from our side, this will be limited to any damage equivalent to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our general terms and condition. Product conformity is guaranteed by properties defined in sales specification. Typical properties do not constitute part of the agreed product property or sales specification. Deviation from typical properties does not constitute non-conformity of the product. Typical properties are provided for general information purpose and as a guideline for the choice of the product; they are subject to variation related to i.e. curing cycles, specimen preparation, batch to batch variability, etc. unless specifically agreed with customers.