

Fiche technique

Thermal Conductive Soft Pad

SPGP600BF

Specification : 300 x 300mm

	Property	SPGP600BF	Unit	Test Method
	Color	Pink/Grey	Visual	--
	Reinforcement Layer	Fiberglass	--	--
	Thickness	0.5~5.0	mm	ASTM D374
	Operating Temperature	-40~+200	°C	--
	Specific Gravity	2.1	g/cm ³	ASTM D792
	Tensile Strength	250	Psi	ASTM D412
	Elongation	10	%	ASTM D412
	Hardness	50 ± 5	Shore OO	ASTM D2240
	Weight Loss	<1	%	200°C@24hrs
	Voltage Breakdown	>10	kV/mm	ASTM D149
	Thermal Conductivity	1.3	W/m.k	ASTM D5470
	Flammability Rating	V-0	--	UL94
	RoHS Compliant	Yes	--	Lab. Certification

* The above testing result comes from testing laboratory report, information for your reference only.