

Thermal Tape-SPGT15

Characteristic :

*Good thermal conductive.

*Good adhesion.

*Easy to assemble.

*Customize size.

	Property	Range	Unit	Test Method
	Color	White	--	Visual
	Reinforce	Fiberglass	--	--
	Thickness	0.15/0.25	mm	ASTM D374
	Operating Temperature	-35 ~ +135	°C	--
	Specific Gravity	1.8 ± 0.2	g/cm ³	ASTM D792
	Hardness	25 ± 1	Shore A	ASTM D2240
	Weight Loss	<1	%	--
	90° Peel test @ 23°C	20/22	N/in	ASTM D3330 Method F
	90° Peel test @ 60°C	25/28	N/in	
	90° Peel test @ 115°C	45/50	N/in	
	Insulation Strength	>2.5/ >4	KV	ASTM D149
	Thermal Conductivity	1.1	W/m.k	ASTM D5470

Storage conditions : Store away from direct sunlight, in cool, dry and ventilated area. 30°C x 60% R↓.

Shelf-life : 1 year.

* The above testing result comes from testing laboratory report, information for your reference only.